# Polypropylene MD231U Polypropylene Compound, Mineral Filled

Description

MD231U is a 20% mineral filled polypropylene compound intended for injection moulding.

This material has excellent balanced mechanical properties and a medium melt flow rate.

## **Applications**

MD231U is designed for:

Air ducts Air filters

\_

Air conditioning parts Automotive under the bonnet parts

# **Special Features**

Long term high heat stabilised UL registered under File E108112 High dimensional stability Low shrinkage

# **Physical Properties**

Property	Typical Value Data should not be used for	Test Method specification work	
Density	1050 kg/m³	ISO 1183	
Melt Flow Rate (230 °C/2,16 kg)	6 g/10min	ISO 1133	
Flexural Modulus (2 mm/min)	2.700 MPa	ISO 178	
Tensile Strength (50 mm/min)	36 MPa	ISO 527-2	
Heat Deflection Temperature B (0,45 MPa)	125 °C	ISO 75-2	
Charpy Impact Strength, notched (23 °C)	3 kJ/m²	ISO 179/1eA	
Charpy Impact Strength, notched (-20 °C)	1 kJ/m²	ISO 179/1eA	

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

# **Application Related and Other Tests**

Property	Typical Value Data should not be used for specifi	Test Method cation work
Fogging (100 °C,16 h)	< 2 mg	DIN 75201
Emission	< 50 µgC/g	VDA 277

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria Telephone +43 1 224 00 0 | Fax +43 1 22 400 333 FN 269858a | CCC Commercial Court of Vienna | Website <u>www.borealisgroup.com</u>





# **Processing Techniques**

The actual conditions will depend on the type of equipment used.

#### **Injection Moulding**

This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following parameters should be used as guidelines:

Feeding temperature Mass temperature Back pressure Holding pressure Mould temperature Screw speed Flow front speed 40 - 80 °C 220 - 260 °C Low to medium 30 - 60 MPa 30 - 50 °C Low to medium 100 - 200 mm/s

## Storage

**MD231** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

# **Regional Availability**

Europe North America For information on regional availability please contact Borealis Sales Representative.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria Telephone +43 1 224 00 0 | Fax +43 1 22 400 333 FN 269858a | CCC Commercial Court of Vienna | Website <u>www.borealisgroup.com</u>





### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria Telephone +43 1 224 00 0 | Fax +43 1 22 400 333 FN 269858a | CCC Commercial Court of Vienna | Website <u>www.borealisgroup.com</u>

