

Product Data Sheet

Sarlink® 3150

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183	950	kg/m ³	950	kg/m ³
Hardness Shore (5 sec delay)	ISO 868	54A		54A	
Extruded sample		56A		56A	
Injection molded sample					
Tensile Properties	ISO 37				
<u>Flow direction</u>					
Tensile strength at break		4.1	MPa	595	Psi
Modulus at 100% elongation		3.0	MPa	435	Psi
Elongation at break		240	%	240	%
<u>Cross direction</u>					
Tensile strength at break		5.1	MPa	740	Psi
Modulus at 100% elongation		1.9	MPa	276	Psi
Elongation at break		600	%	600	%
Tear Strength	ISO 34B				
<u>Cross direction</u>					
Unnicked angle		24	kN/m	137	Pli
Compression set	ISO 815				
22h/23 C		20	%	20	%
22h/70 C		32	%	32	%
70h/125 C		52	%	52	%
Hot air aging	ISO 188				
<u>168h/150 C, Cross Direction</u>					
Change in hardness		2	points	2	points
Retention tensile strength at break		107	%	107	%
Retention modulus at 100% elongation		105	%	105	%
Retention elongation at break		108	%	108	%
<u>1000h/135 C, Cross Direction</u>					
Change in hardness		1	points	1	points
Retention tensile strength at break		94	%	94	%
Retention modulus at 100% elongation		107	%	107	%
Retention elongation at break		93	%	93	%
Volume swell		ISO 1817			
70h/125°C in IRM 903 oil	130		%	130	%
Rheology	ISO 11443				
<u>Apparent Shear Viscosity</u>					
@ 206 1/s, 200 C	Capillary	270	Pa.s	270	Pa.s

* Tests are conducted on injection-molded plaques unless indicated otherwise.

The information and suggestions contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's suggestions. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

© SARLINK® is a registered trademark of Teknor Apex Company
v. 04.2011