

## HTV145

Polypropylene homopolymer

### Technical Support:

Polymer Technology Services Centre  
PO Box 72  
Modderfontein 1645  
South Africa

Tel: +27 (0)11 458 0700  
Fax: +27 (0)11 458 0734

### Sales office:

Sasol Polymers  
PO Box 2525  
Randburg 2125  
South Africa

Tel: +27 (0)11 790 1413  
Fax: +27 (0)11 344 0287

Date of Issue: January 2012

[www.sasol.com/polymers](http://www.sasol.com/polymers)

## Sasol Polymers Polyolefins Business

### Sasol Polymers PP: HTV145

#### Features

- Very high flow
- Narrow molecular weight distribution
- Suitable for the injection moulding of thin walled articles with high flow path / wall thickness ratios
- Contains a nucleating agent which ensures rapid crystallisation, resulting in an improved impact to stiffness balance as well as shorter cooling times
- Suitable for use in extrusion coating processes where the grade offers melt curtain stability and less necking

#### Applications

##### Injection moulding

- Food containers
- Caps and closures
- Pharmaceutical containers
- Thin walled packaging

##### Extrusion

- Extrusion coating of woven PP cloth

### MFR: 50g/10min

#### Additives

- General purpose
- Nucleation
- Mould release


#### Material properties (typical values not to be construed as specifications)

	Value	Unit	Test method
<b>Rheological properties</b>			
Melt mass-flow rate - MFR (230/2.16)	50	g/10min	ISO 1133
Moulding shrinkage - $S_{MP} / S_{MO}$	1.2/1.2	%	ISO 294-4
<b>Mechanical properties</b>			
Flexural modulus	1600	MPa	ISO 178
Tensile modulus of elasticity	1650	MPa	ISO 527-2/1A/1
Tensile stress at yield	35	MPa	ISO 527-2/1A/50
Tensile strain at yield	8.5	%	ISO 527-2/1A/50
Tensile strain at break	>50	%	ISO 527-2/1A/50
Charpy notched impact strength (23°C)	2.5	kJ/m <sup>2</sup>	ISO 179-1/1eA
Ball indentation hardness - HB	75	N/mm <sup>2</sup>	ISO 2039-1
<b>Thermal properties</b>			
Melting temperature - DSC	163	°C	ISO 11357-3
Heat deflection temperature - HDT/A (1.8 MPa)	55	°C	ISO 75-2
Heat deflection temperature - HDT/B (0.45 MPa)	90	°C	ISO 75-2
Vicat softening temperature - VST/A 120 (10N)	155	°C	ISO 306
Vicat softening temperature - VST/B 120 (50N)	92	°C	ISO 306
<b>Other properties</b>			
Density	0.905	g/cm <sup>3</sup>	ISO 1183-1

## Typical processing conditions


### Injection moulding

Melt temperature 220 - 280°C



### Extrusion Coating

Melt temperature 240 - 300°C



## Packaging

Sasol Polymers polyolefin resins are supplied in pellet form packed in 25kg bags. Alternative packaging modes for polypropylene resins are available for selected grades.

## Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses and heat resistant gloves are suggested as a minimal precaution to prevent possible mechanical or thermal injuries to the eyes and skin. Fabrication areas should be ventilated to carry away fumes or vapours.

Conveying equipment should be designed to prevent accumulation of fines or dust particles that are contained in all polyolefin resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. Sasol Polymers recommend the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

Sasol Polymers further recommend that good housekeeping be practised throughout the manufacturing facility. Polymer pellets may pose a slippage hazard if spilled.

## Storage

As ultraviolet light may cause a change in the material properties, all polyolefin resins should be protected from direct sunlight during storage. Under cool, dry, dark conditions Sasol Polymers polyolefin resins are expected to maintain their original material and processing properties for at least 18 months.