

Product Data Sheet

TL-3071-80A

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183		kg/m ³		kg/m ³
Hardness Shore (5 sec delay) Injection molded sample	ISO 868	80A	1320	80A	1320
Tensile Properties Tensile strength at break Modulus at 100% elongation Elongation at break	ISO 37	6.6 3.6 700	MPa MPa %	957 522 700	Psi Psi %
Compression set 22h/70° C	ISO 815	64	%	64	%
Rheology <u>Apparent Shear Viscosity</u> @ 206 1/s, 200° C	ISO 11443 Capillary	222	Pa.s	222	Pa.s

* Tests are conducted on injection-molded plaques unless indicated otherwise.

* Typical values: Not to be construed as specification.