

# Product Data Sheet

## TL-3071-70A

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183		kg/m <sup>3</sup>		kg/m <sup>3</sup>
Hardness Shore (5 sec delay) Injection molded sample	ISO 868	70A	1320	70A	1320
<b>Tensile Properties</b> Tensile strength at break Modulus at 100% elongation Elongation at break	ISO 37	5.4 2.9 700	MPa MPa %	783 421 700	Psi Psi %
Compression set 22h/70° C	ISO 815	62	%	62	%
<b>Rheology</b> <u>Apparent Shear Viscosity</u> @ 206 1/s, 200° C	ISO 11443 Capillary	172	Pa.s	172	Pa.s

\* Tests are conducted on injection-molded plaques unless indicated otherwise.

\* Typical values: Not to be construed as specification.